



PyzoFlex[®]

Make your surface smart!



PyzoFlex®



Design-driven

- Any surface
- Any material
- Any design



Flexible

- Light and thin surface
- Formable
- Resistant against environmental damages




Intelligent

- Real-time
- Application specific
- Customized



Energy

- Passive
- Harvesting
- Low temperature processing



Dynamic

- Pressure
- Temperature
- Vibro-acoustics

Use Cases



User Interfaces

- New interaction: e.g. by deformation, touch interface on any surface
- Freedom of design
- Operating with gloves possible
- Cost-efficient



Smart Environment

- Integrable in any surface
- Application-specific intelligence
- Measurement of pressure and temperature changes
- Energy harvesting



Safety Systems


- Industrial automation
- Smart buildings
- Active & assisted living

Sensor Applications




Piezoelectric sensing

- Pressure changes
- Acoustics/vibro acoustics
- Structure borne sound
- Impact analytics
- Force lines, threshold forces




Pyroelectric sensing

- Temperature changes
- Waste heat detection
- Thermal gradients
- Laser detection
- Proximity sensing




Flexible sensors

- Bending
- Wavelike movements
- Curved surfaces
- Smart skin
- Wearables



Energy harvesting

- Body movement
- Vibrations
- Temperature changes
- Deformations
- Wind, tides



Vibro acoustic sensing






- Vibration Analysis
- Condition Monitoring
- Acoustic Event Detection
- Structural Health Analysis
- Vibration-based Interaction

Scientific Excellence & Awards



patented!

Standard fabrication process by screen-printing

Substrate	1 st Electrode	Active Material	2 nd Electrode	Connections
				
Plastic, paper, textile, glass, metal, transfer foils ...	PEDOT: PSS (conductive, transparent polymer)	Copolymer: PVDF:TrFE-Ink patented!	PEDOT:PSS (for semi-transparent sensors) Carbon	Ag lines for connection to read-out electronics


Key Facts: Sensor-Fabrication

- Minimal sensor thickness 6µm
- Quality control by poling process
- Printable on versatile substrates (low temperature fabrication < 100°C)
- Substrate sizes up to 420 x 420mm with a thickness ≤ 20mm
- Semi-transparent sensors if solely PEDOT:PSS is used as electrode material
- Cost efficient sheet to sheet manufacturing by industrial screen printing process
- Application specific sensor shapes based on CAD designed screen masks (max. resolution = 12000dpi)
- Feature sizes down to 100µm (depending on material and screen)

Key Facts: Printing Equipment

- Thieme LAB 1000
- Alignment accuracy: (±) 10µm
- Full camera alignment
- High reproducibility due to software control
- Monitoring of printing parameters
- Process transfer to industrial lines

ON THE ROAD TO MASS-PRODUCTION



Key Facts Technology

Measured physical properties of screen-printed PyzoFlex® sensors based on PVDF:TrFE=70:30				
	min.	typical	max.	Unit
Recommended poling field	100	150	200	MV/m
Displacement	50	60	66	mC/m ²
Coercive field @ 10Hz	46	55	60	MV/m
Pyroelectric coefficient @ 25°C	28,5	34	37,5	μC/m ² K
Pyroelectric coefficient from -90°C to +90°C	12 — 52	15 — 62	16 — 67	μC/m ² K
Piezoelectric coefficient d₃₃	-21	-25	-27,4	pC/N
Tested pressure range*	30m — 40k			N/cm ²
Electromechanic coupling coefficient k₃₃ (1Hz — 1kHz)*	0,15	0,16	0,17	-
Curie Temperature	103	104	105	°C
Standard PVDF:TrFE layer thickness	3	5	15	μm
Capacity at standard layer thickness	2	1,33	0,45	nF/cm ²
Capacity (thickness normalized)	6,21	6,64	6,79	nF/cm ² μm ⁻¹
Permittivity @ 1kHz (poled)	7,2	7,5	7,9	-
Permittivity @ 1kHz (unpoled)	10,9	11,4	12,0	-
Frequency response**	100μ — 1M			Hz
Tunable properties based on polymer-composition				
VDF content of PVDF:TrFE	55, 70, 80			%mol
Curie temperature	62 — 132			°C
Coercive field (quasi-static)	46 — 57			mV/m
Displacement	48 — 80			mC/m ²
Piezoelectric coefficient d₃₃	-26 — -30			pC/N

* Due to the flexibility of PyzoFlex®, the conversion of force to mechanical deformation can be enhanced by employing appropriate mechanical design.

** The parameter limits are determined by available measurement equipment and its measurement ranges.

The technology is based on ferroelectric polymers, which are applied using a cost-effective screen printing method. These films can detect localized pressure and temperature changes with high precision. The performance of the PyzoFlex® technology within specific applications strongly depends on the mechanical design (conversion of external stimuli into tiny mechanical deformations) and therefore cannot be generalised. All the data presented within this data sheet are based on measurements of PyzoFlex®-sensors composed of the ferroelectric copolymer PVDF:TrFE = 70:30 printed on PET-substrates.

Ageing analysis of PyzoFlex®

Test ID	Test name	Description
TS	Temperature Storage	Keeping samples at 105°C for 24 hours
HW	Hot Water Test	Keeping samples in water at 99.9°C for 1 hour
1000H	1000 Hours Test	Keeping samples at 85°C and 85% humidity for 1000 hours (42 days)
ThSh	Thermal Shock	The samples are kept at alternating low and high temperatures. During the cold phase the samples are kept at -40°C for 30 min. During the hot phase they are kept at +85°C for 30 min. The test lasts 11 days.
UP	Uniaxial Pressure Test	A static pressure of 0.1 MPa is applied for 240 hours (10 days) at 85°C
MA	Multiple Mechanical Actuation Test	106 actuations are performed at a frequency of 1Hz. Within each actuation the pressure of p=0.01MPa at room temperature is applied.
Shr.	Shrinkage Test	A sample of a fixed size is placed into an oven at 90°C for 30 min and the ratio of the size after and before the test is determined.
Fl.	Flammability Test	The sample stripe of a prescribed length is set afire; the speed of the flame front is measured and classified by integers from 0 to 5.
BC	Bending Cycles	4 million bending cycles (deflection ± 1cm) without degradation.
PC	Pressure Cycles	2.5 million pressure loads (9N/cm ²) without degradation.
QC	Quality Control	Quality controlled process by quantitative poling procedure.

According to the tested parameters PyzoFlex® has potential for automotive applications.

Measuring principle of PyzoFlex® – mechanical to electrical

Like all piezoelectric materials, the PyzoFlex® polymer transducer develops an electrical charge proportional to a change in mechanical stress. The amplitude and frequency of the signal is directly proportional to the mechanical deformation of the material, resulting in a change in the surface charge density of the material so that a voltage appears between the electrode surfaces. When the force is reversed, the output voltage is of opposite polarity. An alternating force therefore results in an alternating output voltage. PyzoFlex® is not suitable for static measurements as the electrical charges developed decay with a time constant that is determined by the dielectric constant and the internal resistance of the transducer, as well as the input impedance of the interface electronics to which the transducer is connected resulting in a minimal frequency measurable in the order of 0.001Hz. There are methods to achieve static measurement, but these require using PyzoFlex® as both an actuator and sensor, monitoring change in the actuation. The fundamental piezoelectric coefficients for charge or voltage predict, for small stress (or strain) levels, the charge density (charge per unit area) or voltage field (voltage per unit thickness) developed by the transducer. A properly designed interface circuit plays a key role in the optimization of PyzoFlex® transducers.

In cooperation with:



CONTACT

JOANNEUM RESEARCH
Forschungsgesellschaft mbH
8010 Graz, Austria
Phone +43 316 876-3000

PyzoFlex[®]

pyzoflex@joanneum.at
www.joanneum.at/pyzoflex